

FabPro™ 1000 Industrial-Grade Desktop 3D Printer



FabPro 1000

Build Volume (xyz)	125 x 70 x 120 mm (4.92 x 2.76 x 4.72 in)*
Pixel Pitch	65 microns (.0025 in) (390.8 effective DPI)
Wavelength	405 nm
Build Materials	FabPro Tough BLK, FabPro Proto GRY, FabPro JewelCast GRN
Operating Environment Temperature Humidity (RH)	18 - 28 °C (64-82 °F) 30 - 70 %
Electrical Input Output	100-240v, AC, 50/60Hz 24V DC, 3.75 A; with power supply
Dimensions (WxDxH) 3D Printer with packaging 3D Printer without packaging	80 x 80 x 94 cm (31.5 x 31.5 x 37 in) 43 x 43 x 61.2 cm (16.9 x 16.9 x 24.1 in)
Weight 3D Printer with packaging 3D Printer without packaging	58 kg (127.87 lbs) 37.5 kg (82.67 lbs)
3D SPRINT™ Software	Easy build job set-up, submission and job queue management; Automatic part placement and build optimization tools; Part nesting capability; part editing tools; Automatic support generation; Job statistics
Connectivity	Network ready with 10/100/1000 BaseT Ethernet interface USB (direct printing)
Client Operating Systems	Windows® 7, Windows 8 or Windows 8.1 (Service Pack), Windows 10 (64-bit OS supported)
Input Data File Formats Supported	STL, CTL, OBJ, PLY, ZPR, ZBD, AMF, WRL, 3DS, FBX, IGES, IGS, STEP, STP, X_T
Post-Processing	Includes part finishing tools accessory kit; requires optional 3D Systems LC-3DPrint Box UV post-curing unit or other UV-curing unit
Certifications	FCC, CE, EMC
Accessories	LC-3DPrint Box UV post-curing unit, LC-3DMixer



FabPro™ Materials

For prototyping, engineering and jewelry applications



	FabPro Tough BLK	FabPro Proto GRY	FabPro JewelCast GRN
Description	Tough production plastic	Fast, general purpose	Master patterns for gypsum investment casting
Color	Black	Gray	Green
Bottle Volume	1 kg	1 kg	1 kg
Layer Thickness	0.050 mm 0.002 in	0.050 mm 0.002 in	0.030 mm 0.001 in
Vertical Build Speed	14 mm/hr 0.55 in/hr	21 mm/hr 0.83 in/hr	5.3 mm/hr 0.21 in/hr
Liquid Density	1.05 g/cm ³	1.04 g/cm ³	1.10 g/cm ³

Cured Part Properties*		FabPro Tough BLK		FabPro Proto GRY		FabPro JewelCast GRN	
		Metric	U.S.	Metric	U.S.	Metric	U.S.
Solid Density		1.12 g/cm ³	0.040 lb/in ³	1.13 g/cm ³	0.041 lb/in ³	1.18 g/cm ³	0.043 lb/in ³
Tensile Strength	ASTM D638	44 MPa	64 psi	67 MPa	9700 psi	14 MPa	2000 psi
Tensile Modulus	ASTM D638	1860 MPa	270 ksi	2800 MPa	410 ksi	355 MPa	51.5 ksi
Elongation at Break	ASTM D638	44 %	44 %	7 %	7 %	10 %	10 %
Flexural Modulus	ASTM D790	2020 MPa	290 ksi	2840 MPa	410 ksi	577 MPa	84 ksi
Flexural Strength	ASTM D790	64 MPa	9700 psi	100 MPa	14500 psi	14 MPa	2030 psi
Izod Notched Impact	ASTM D256	36 J/m	0.7 ft-lb/in	23 J/m	0.4 ft-lb/in		
Izod Unnotched Impact	ASTM D256	568 J/m	11 ft-lb/in	123 J/m	2.3 ft-lb/in		
Water Absorption (24 hours)	ASTM D570	0.3 %	0.3 %	0.25 %	0.25 %		
Tg	DMA, E''	57 °C	134 °F	82 °C	180 °F	-1 °C	31 °F
Heat Deflection Temperature @0.46 MPa 66 psi @1.82 MPa 264 psi	ASTM D648	48 °C	119 °F	79 °C	175 °F		
		42 °C	107 °F	66 °C	151 °F		
CTE >Tg CTE <Tg	ASTM E831	130 ppm/°C	72 ppm/°F	107 ppm/°C	59 ppm/°F	185 ppm/°C	102 ppm/°F
		161 ppm/°C	89 ppm/°F	111 ppm/°C	62 ppm/°F	169 ppm/°C	94 ppm/°F
Shore Hardness	ASTM D2240	79 D	79 D	83 D	83 D	68 D	68 D

* All properties measured on new material processed according to 3D Systems standard user recommendations

DISCLAIMER: It is the responsibility of each customer to determine that its use of any FabPro material is safe, lawful and technically suitable to the customer's intended applications. The values presented here are for reference only and may vary. Customers should conduct their own testing to ensure suitability for their intended application.



Print the Future

3DZ Franchising (Malta)
 3DZ Treviso (Castelfranco Veneto)
 3DZ Brescia (Rezzato)
 3DZ Piedmont (Casale Monferrato)
 3DZ Rome (Rome)
 3DZ Tuscany (Arezzo)
 3DZ Emilia (Reggio Emilia)
 3DZ Albania (Tirana)
 3DZ Hungary (Budapest)
 3DZ Romania (Craiova)
 3DZ Barcelona (Spain)
 3DZ Andalusia (Spain)
 3DZ Madrid (Spain)
 3DZ Serbia (Belgrade)
 3DZ Dubai (Dubai)

(+356) 2713 915 2
 (+39) 0423 192307 0
 (+39) 030 638519 5
 (+39) 0142 23109 1
 (+39) 06 3973683 5
 (+39) 057 590854 2
 (+39) 0522 51695 0
 (+355) 688 08783 0
 (+36) 1 794343 2
 (+40) 251 41976 4
 (+34) 938 441 720
 (+34) 953 88 80 89
 (+34) 912 24 30 84
 (+381) 11 265199 0
 (+941) 4251773 4

info@3dz.com mt
 tv@3dz.it
 bs@3dz.it
 to@3dz.it
 roma@3dz.it
 info@tbnnet.it
 re@3dz.it
 tirana@3dz.al
 budapest@3dz.hu
 contact@cadworks.ro
 barcelona@3dz.es
 info@3dz.es
 madrid@3dz.es
 info@solfins.com
 info@3dz.com mt